

## Standard (non-activated) 3A, 4A, 5A and 13X Zeolite Powders

Product Code	Cation	H <sub>2</sub> O Ads. RH50%, 25C	CO <sub>2</sub> Ads. 250mm, 25C	LOI wt%	Part. Size micron	Density g/ml	Notes
<b>3A-38</b>	K > 38%	> 25.5		< 21	3-5	> .70	Standard
<b>3A-45</b>	K > 45%	> 25.5		< 21	3-5	> .70	
<b>3A-60</b>	K > 60%	> 23.5		< 21	3-5	> .70	High K
<b>3A-D-38</b>	K > 38%	> 25		< 21	6-9	> .78	Hi Density
<b>3A-D-45</b>	K > 45%	> 25		< 21	6-9	> .78	Hi Density
<b>4A</b>	Na	> 27		< 21	3-5	> .70	Standard
<b>4A-D</b>	Na	> 26.5		< 21	6-9	> .75	Hi Density
<b>4A-5</b>	Na	> 27		< 21	< 3	> .65	Hi Capacity
<b>5A-70</b>	Ca > 70%	> 27		< 21	3-5	> .70	Standard
<b>5A-90</b>	Ca > 90%	> 27		< 21	3-5	> .70	Standard
<b>5A-D-70</b>	Ca > 70%	> 27		< 21	6-9	> .75	Hi Density
<b>5A-D-90</b>	Ca > 90%	> 27		< 21	6-9	> .75	Hi Density
<b>13X</b>	Na	> 32	> 22.5	< 23	3-5	> .60	Standard
<b>13X-D</b>	Na	> 32	> 22.5	< 23	6-8	> .68	Hi Density
<b>13X-5</b>	Na	> 32	> 22.5	< 23	< 3	> .58	Hi Capacity
<b>13X-L</b>	Na	> 32	> 22.5	< 23	3-5	> .60	Low Chloride
<b>13X-B</b>	Na	> 32	> 22.5	< 23	4-6	> .60	Benzene Grade
<b>13X-C</b>	Na	> 32	> 23	< 23	4-6	> .60	Hi Stability

**EURECAT - Zeolites, Molecular Sieves and Custom Catalysts**

Tel: +1 281 218 0669  
Fax: +1 281 218 9850

**Headquarters**  
1331 Gemini Street  
Houston, Texas 77058

www.eurecat.com  
sales@eurecat.com